



**FUZION™**  
TECHNOLOGIES, INC.

WWW.FUZIONTECHNOLOGIES.US

**Freeport Brick Division**  
**Kittanning Brick Division**  
P.O. Box 338  
Freeport PA 16229  
724-295-2800  
Fax 724-295-2815

**Memphis Division**  
4126 Delp Street Suite 200  
Memphis TN 38118  
901-365-6632

## TECHNICAL DATA F28 (BARRIER BRICK)

November, 2011

Pyrometric Cone Equivalent	26
Porosity	15 %
Bulk Density	2.18 g/cc 135.9 lb/cu ft
Modulus of Rupture	1000 psi
Cold Crushing Strength	6000 psi
Thermal conductivity W/mK @ 200°C	0.75
@ 600°C	0.91
Calcined Basis Chemical Analysis:	
SiO <sub>2</sub>	64.7%
Al <sub>2</sub> O <sub>3</sub>	28.0%
TiO <sub>2</sub>	1.6%
Fe <sub>2</sub> O <sub>3</sub>	2.3%
CaO	0.4%
MgO	0.5%
Na <sub>2</sub> O	0.2%
K <sub>2</sub> O	2.2%
P <sub>2</sub> O <sub>5</sub>	traces

The information contained in this bulletin are average tests results determined by ASTM Test Procedures and are subject to normal variation or individual tests. All data is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance.