



FUZION™
TECHNOLOGIES, INC.

WWW.FUZIONTECHNOLOGIES.US

Freeport Brick Division
Kittanning Brick Division
P.O. Box 338
Freeport PA 16229
724-295-2800
Fax 724-295-2815

Memphis Division
4126 Delp Street Suite 200
Memphis TN 38118
901-365-6632

TECHNICAL DATA STIFF MUD WIRE CUT

August, 2011

Water Absorption	5%
Porosity	12 %
Bulk Density g/cc	2.27
Modulus of Rupture	1500 psi
Compressive Strength	10000 psi
Abrasion Resistance	1.0 cc
Calcined Basis Chemical Analysis:	
SiO ₂	64.0%
Al ₂ O ₃	27.8%
TiO ₂	1.6%
Fe ₂ O ₃	1.2%
CaO	1.2%
MgO	1.2%
Na ₂ O	0.3%
K ₂ O	2.2%
P ₂ O ₅	traces

The information contained in this bulletin are average tests results determined by ASTM Test Procedures and are subject to normal variation or individual tests. All data is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance.