



FUZION™
TECHNOLOGIES, INC.

WWW.FUZIONTECHNOLOGIES.US

Freeport Brick Division
Kittanning Brick Division
P.O. Box 338
Freeport PA 16229
724-295-2800
Fax 724-295-2815

Memphis Division
4126 Delp Street Suite 200
Memphis TN 38118
901-365-6632

TECHNICAL DATA SHALE ACID BRICK TYPE II

August, 2011

Water Absorption	4%
Porosity	8%
Bulk Density	2.35 g/cc
Apparent Specific Gravity	2.55
Modulus of Rupture	2000 psi
Cold Crushing Strength	16000 psi
Acid Solubility	less than 8%

Calcined Basis Chemical Analysis:

SiO ₂	64.21%
Al ₂ O ₃	22.06%
TiO ₂	0.97%
Fe ₂ O ₃	6.32%
CaO	0.32%
MgO	1.92%
Na ₂ O	0.30%
K ₂ O	3.90%

The information contained in this bulletin are average tests results determined by ASTM Test Procedures and are subject to normal variation or individual tests. All data is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance.