



FUZION[™]
TECHNOLOGIES, INC.

www.fuziontechnologies.us

Freeport Brick Division
P.O. Box 338
Freeport PA 16229
724-295-2800
Fax 724-295-2815

Kittanning Brick Division
R.D. #1, Box 279
Adrian PA 16210
724-543-1200
Fax 724-868-2721

Armstrong Precision Manufacturing Division
114 West Park Drive
Kittanning PA 16201
724-545-2223
Fax 724-543-2592

Fuzion - Memphis
4126 Delp Street Suite 200
Memphis TN 38118
901-365-6632

TECHNICAL DATA

DURO DOT

August, 2008

Pyrometric Cone Equivalent	26
Porosity	16 %
Bulk Density	2.20 g/cc 137 lb/cuft
Modulus of Rupture	1000 psi
Cold Crushing Strength	5000 psi
Abrasion Resistance C704	1.0%
Calcined Basis Chemical Analysis:	
SiO ₂	65.50%
Al ₂ O ₃	29.16%
TiO ₂	1.6%
Fe ₂ O ₃	2.3%
CaO	0.3%
MgO	0.8%
Na ₂ O	0.18%
K ₂ O	0.16%
P ₂ O ₅	traces

The information contained in this bulletin are average tests results determined by ASTM Test Procedures and are subject to normal variation or individual tests. All data is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance.